

		Filter Media													Housing			
		Cellulose Acetate	Nitrocellulose	Glass Fiber (binder)	Glass Fiber (no binder)	Polyethersulfone	RC	PVDF Philic	Nylon	Polycarbonate	Polyester	Polypropylene	PTFE (unlaminated)	PTFE (laminated)	Silver	Modified Acrylic	Polysulfone	Polystyrene
R= Recommended L= Limited Resistance (testing before use is recommended) N= Not Recommended T= Test																		
<b>ACIDS</b>	Acetic Acid 5%	R	R	T	R	R	R	R	R	R	R	R	R	R	R	N	R	R
	Acetic Acid 10%	N	N	T	R	R	N	R	L	R	R	R	R	R	R	N	R	R
	Acetic Acid, Glacial	N	N	N	R	R	N	R	N	L	R	R	R	R	R	N	R	R
	Boric Acid	R	R	T	T	T	R	T	L	R	R	R	R	R	R	N	R	R
	Hydrochloric, 6N	L	N	N	R	R	N	L	N	R	L	R	R	R	R	N	R	R
	Hydrochloric, Conc.	N	N	N	R	R	N	R	N	R	N	R	R	R	R	N	R	R
	Hydrofluoric, 10%	N	N	N	N	T	N	R	N	R	R	R	R	R	R	T	T	T
	Hydrofluoric, 35%	N	N	N	N	T	N	R	N	R	R	T	R	T	R	T	T	T
	Nitric Acid, 6N	L	R	N	L	N	R	T	N	R	R	L	R	L	N	N	N	L
	Nitric Acid, Conc.	N	N	N	L	N	N	R	N	R	N	N	R	N	N	N	N	N
	Sulfuric Acid, 6N	L	R	N	R	T	R	R	N	R	R	L	R	L	N	N	N	N
	Sulfuric Acid, Conc.	N	N	N	R	N	N	T	N	N	N	N	R	N	N	N	N	N
<b>ALCOHOLS</b>	Amly Alcohol	R	N	R	R	N	N	R	R	R	R	R	R	R	R	N	R	N
	Benzyl Alcohol	L	R	N	N	N	R	R	L	L	R	R	R	R	R	R	R	N
	Butyl Alcohol	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R	T
	Butyl Cellosolve	L	N	R	R	T	N	T	R	L	R	R	R	R	R	T	L	T
	Ethyl Alcohol <80%	R	R	R	R	R	R	R	R	R	R	R	R	R	R	L	R	L
	Ethyl Alcohol >80%	R	L	R	R	R	L	R	R	R	R	R	R	R	R	L	R	N
	Ethylene Glycol	R	L	R	R	R	L	R	R	R	R	R	R	R	R	T	R	T
	Glycerine (Glycerol)	R	R	R	R	R	R	R	R	R	R	R	R	R	R	T	R	T
	Isobutyl alcohol	R	R	N	N	T	R	R	R	R	R	R	R	R	R	R	R	R
	Isopropanol	R	L	R	R	R	L	R	R	R	R	R	R	R	R	T	R	T
	Methanol	R	N	R	R	R	N	R	L	R	R	R	R	R	R	R	R	R
	Methyl Cellosolve	L	L	R	R	T	L	R	R	N	R	R	R	R	R	T	R	T
	Propanol	R	R	R	R	T	R	R	R	R	R	R	R	R	R	T	R	T
<b>BASES</b>	Ammonium Hydroxide, 6N	N	N	N	R	R	N	R	N	N	L	R	R	R	R	R	R	R
	Potassium Hydroxide, 6N	N	N	N	T	T	N	R	R	N	N	R	R	R	R	T	R	T
	Sodium Hydroxide, 6N	N	N	N	T	R	N	R	N	N	L	R	R	R	R	T	T	T
<b>SOLVENTS</b>	Acetone	N	N	R	R	N	N	N	R	L	R	R	R	R	R	N	N	N
	Acetonitrile	N	N	T	R	R	N	R	R	L	R	R	R	R	T	N	N	N
	Amyl Acetate	L	N	N	R	L	N	R	R	R	R	R	R	R	R	N	N	N
	aniline	N	N	T	T	R	N	T	R	N	R	R	R	R	R	T	N	T
	Benezene	L	R	N	R	R	R	R	R	L	R	L	R	L	R	N	N	N
	Bromoform	N	R	R	R	T	R	T	R	N	R	R	R	R	R	T	N	T
	Butyl Acetate	L	N	N	R	L	N	T	R	R	R	R	R	R	R	N	N	N
	Carbon Tetrachloride	L	R	N	N	R	R	R	R	L	R	L	R	L	R	N	N	N
	Cellosolve	R	N	R	R	T	N	T	R	R	R	R	R	R	R	N	N	T
	Chloroform	N	R	R	R	N	R	R	R	N	R	L	R	L	R	N	L	N
	Cyclohexane	R	R	R	R	T	R	T	R	R	R	R	R	R	R	N	R	T
	Cyclohexanone	N	N	R	R	N	N	N	R	L	R	R	R	R	R	N	N	N
	Diethyl Acetamide	N	N	R	R	T	N	T	R	L	R	N	R	N	R	N	N	N
	Dimethyl Formamide	N	N	N	R	N	N	N	R	N	R	R	R	R	R	N	N	N
	Dimethyl Sulfoxide (DMSO)	N	N	N	R	N	N	N	R	N	R	R	R	R	T	N	N	N
	Dioxane	N	N	R	R	L	N	R	R	N	R	R	R	R	R	N	N	N
	Ethyl Ether	L	L	T	R	R	L	R	R	R	R	R	R	R	R	N	L	N
	Ethylene Dichloride	L	L	R	R	T	L	T	R	N	R	R	R	R	R	T	N	T
	Formaldehyde	L	N	R	R	R	N	R	R	R	R	R	R	R	R	N	R	N
	Freon TF	R	R	R	R	R	R	R	R	R	R	R	R	R	R	L	R	N
	Gasoline	R	R	R	R	T	R	R	R	R	R	R	R	R	R	N	R	N

		Filter Media													Housing			
		Cellulose Acetate	Nitrocellulose	Glass Fiber (binder)	Glass Fiber (no binder)	Polyethersulfone	RC	PVDF Philic	Nylon	Polycarbonate	Polyester	Polypropylene	PTFE (unlaminated)	PTFE (laminated)	Silver	Modified Acrylic	Polysulfone	Polystyrene
R= Recommended L= Limited Resistance (testing before use is recommended) N= Not Recommended T= Test																		
	Hexane	R	R	L	R	T	R	R	R	R	R	R	R	R	R	N	R	N
	Isopropyl Acetate	N	N	N	R	T	N	N	R	R	R	R	R	R	R	N	N	N
	Kerosene	R	R	R	R	T	R	R	R	R	R	R	R	R	R	N	N	N
	Methyl Acetate	N	N	N	R	T	N	R	R	N	R	R	R	R	R	N	N	N
	Methyl Ethyl Ketone (MEK)	N	N	R	R	N	N	NR	R	L	R	R	R	R	R	N	N	N
	Methyl Isobutyl Ketone	N	N	R	R	T	N	N	R	L	T	R	R	R	R	N	N	N
	Methylene Chloride	N	N	R	R	N	N	R	L	N	R	R	R	R	R	N	N	N
	Nitrobenzene	N	N	N	N	N	N	R	R	N	R	R	R	R	T	N	N	N
	Pentane	R	R	R	R	R	R	R	R	R	R	L	R	L	R	N	R	N
	Perchloroethylene	R	R	N	N	N	R	T	R	R	T	R	R	R	R	N	L	N
	Pyridine	N	N	N	R	N	N	N	R	N	R	R	R	R	R	N	N	N
	Tetrahydrofuran	N	N	T	L	N	N	N	L	N	R	L	L	L	R	N	N	N
	Toluene	L	R	N	R	N	R	R	R	L	R	L	R	L	R	N	N	N
	Trichloroethane	L	N	T	T	R	N	T	R	N	T	R	R	R	R	N	N	N
	Trichlorethylene	R	R	N	N	R	R	R	R	B	R	L	L	L	R	N	N	N
	Triethylamine	R	L	R	R	T	L	T	R	L	R	R	R	R	R	T	N	T
	Xylene	R	R	R	R	L	R	R	R	R	R	L	R	L	R	N	N	N
<b>MISCELLANEOUS</b>	Cottonseed Oil	R	R	L	R	T	R	T	R	R	T	R	R	R	R	T	R	T
	Hydrogen Peroxide (30%)	R	R	R	R	T	R	R	R	R	R	R	R	R	R	T	R	T
	Kodak KMER FTFR	N	N	N	N	T	N	T	R	R	R	R	R	R	R	N	R	N
	Peanut Oil	R	R	R	R	T	R	T	R	R	R	R	R	R	R	T	R	T
	Petroleum Oils	T	R	T	T	L	R	R	T	R	R	T	R	T	R	T	T	T
	Sesame Oil	R	R	R	R	T	R	T	R	R	R	R	R	R	R	T	R	T
	Shipley (AS-111,340,1350)	N	N	N	N	T	N	T	R	R	R	R	R	R	R	N	R	N
	Silicone Oils	R	R	R	R	R	R	R	R	R	R	R	R	R	R	T	R	T
	Turpentine	R	R	R	R	T	R	T	R	R	R	R	R	R	R	T	R	T
	Waycoat 59	N	N	N	N	T	N	T	R	R	R	R	R	R	N	R	N	